Aqua-Deck HPX

Eco-friendly, water-based oil-resin for the treatment of floors and wooden products in external applications.

Aqua-Deck HPX develops high levels of protection and resistance to atmospheric agents for external wood floors and products. <image><image><image><image>

- 1. Applicable with a brush or roller
- 2. Rapid drying and overlaying
- 3. Compliant with Directive 2004/42/EC

Rating 4

× VOC Low Emission

BUILDING REF. GBR DATA

REPORT 06.23

PPROVE

NG

- ✓ Water Based
- \checkmark Solvent $\leq 80 \text{ g/kg}$
- Low Ecological Impact
- ✓ Health Care

kerakoll

Areas of application

- \rightarrow Intended use:
 - High protection finish for:
 - external wood flooring generally used around pools and on decks, terraces, and walkways
 - external wood products

External wood flooring and products in residential and commercial buildings.

Do not use directly on previously treated flooring and products that have not been sanded down properly.

Instructions for use

\rightarrow Preparation of substrates

The wood must be dry and have a humidity value that meets the manufacturer's recommendations. Buff or sand the hardwood floors until the surface is smooth, clean and free from oil, grease, wax, silicon and previous coats of varnish. Perform the final sanding using abrasives from the Duraflex or Carbodur range in 100/120 grain for a smooth appearance, or 60/80 grain for a rougher surface with non-slip effect.

Carefully remove any dust created during sanding and wipe away any residues using a Pulex antistatic cloth, then apply Aqua-Deck HPX.

 \rightarrow Preparation

The product is ready-to-use. Shake thoroughly before use, insert the undercap filter and pour into the appropriately prepared tray. Remove the undercap filter before shutting the can. \rightarrow Application

Apply Aqua-Deck HPX as it is with a coverage of $\approx 100 \text{ ml/m}^2$. Apply the second coat of Aqua-Deck HPX as soon as the floor can take foot traffic ($\approx 4 - 6$ h). Once the product is completely dry ($\approx 6-8$ hrs within 16-24 hrs), apply the third coat of Aqua-Deck HPX. Lay the product crossways creating portions of floor with a maximum width of 3-4 floor elements (max 30 cm) and uniform the laying lengthwise.

 \rightarrow Cleaning

Clean away any residue of Aqua-Deck HPX with Roller Clean before it hardens. Once hardened, Aqua-Deck HPX can only be removed mechanically.

Special notes

- \rightarrow Use clean containers and tools.
- \rightarrow For an even finish, apply evenly in accordance with the recommended quantities.
- → It is recommended that a preliminary test be carried out on the wood to be treated in order to check the final aesthetic effect.
- \rightarrow Apply Aqua-Deck HPX avoiding direct sunlight.
- \rightarrow Do not proceed with the application if rain is forecast in the following 24 hours.

Abstract

Weatherproofing treatment for external wood flooring and products to provide high protection and resistance to atmospheric agents. It will be carried out using a single-component, eco-friendly water-based resin-oil compliant with Directive 2004/42/EC, GreenBuilding Rating 4, such as Aqua-Deck HPX by Kerakoll Spa, applied by roller in three coats of $\approx 100 \text{ ml/m}^2 \text{ per coat}.$

| Technical Data compliant with Kerakoll Quality Standard | |
|---|---|
| Appearance | amber-coloured liquid |
| Pack | can 5 l |
| Shelf life | \approx 12 months from production in the original sealed packaging |
| Warning | protect from frost, avoid direct exposure to sunlight and sources of heat |
| Temperature range for application | from +5 °C to +30 °C |
| Interval before normal use: | |
| - for light foot traffic | ≈ 36 – 48 h |
| - for normal foot traffic | ≈ 7 – 10 days |
| Coverage | $\approx 100 \text{ ml/m}^2 \text{ per coat}$ |

Values taken at +23 °C, 50% R.H. and no ventilation. Data may vary depending on specific conditions at the building site, i.e. temperature, ventilation and absorbency level of the substrate.

Warning

- \rightarrow Product for professional use
- \rightarrow abide by any standards and national regulations
- → check compatibility (colour, the content of resins, oils and other substances) with less common woods
- \rightarrow remove all residues of previous treatments to ensure an even finish
- \rightarrow if necessary, ask for the safety data sheet
- → for any other issues, contact the Kerakoll Worldwide Global Service +39 0536 811 516 globalservice@kerakoll.com



The Rating classifications refer to the GreenBuilding Rating Manual 2013. This information was last updated in June 2023 (ref. GBR Data Report - 06.23); please note that additions and/ or amendments may be made over time by KERAKOLL SpA; for the latest version, see www.kerakoll.com. KERAKOLL SpA shall therefore be liable for the validity, accuracy and updating of information provided only when taken directly from its institutional website. The technical data sheet given here is based on our technical and practical knowledge. As it is not possible for us to directly check the conditions in your building site and the execution of the work, this information represents general indications that do not bind Kerakoll in any way. Therefore, it is advisable to perform a preliminary test to verify the suitability of the product for your purposes.