

Biogel No Limits

Exclusive Kerakoll geo-binder based, structural flexible multi-purpose gel adhesive for bonding all types of material, on all substrates, and for all use, even in extreme conditions.



1. Thixotropic and fluid
2. Full wettability
3. High deformability
4. Specifically intended for laying large slabs

Rating 4^{White}
Rating 3^{Grey}



W G

- × × Regional Mineral ≥ 60%
- ✓ × Recycled Regional Mineral ≥ 30%
- ✓ ✓ CO₂ Emission ≤ 250 g/kg
- ✓ ✓ VOC Low Emission
- ✓ ✓ Recyclable

Areas of application

→ Use

Substrates No Limits:

- existing tiles
- waterproofing products
- heated floors
- cement-based screeds and self-levelling products
- lime and cement-based plasters/renders
- concrete
- cellular concrete
- plasterboard
- gypsum and anhydrite (1)
- to overlay existing floors
- fibro-cement slabs
- thermal insulation panelling systems
- insulating panels
- timber ⁽¹⁾
- metal ⁽¹⁾
- PVC ⁽¹⁾

(1) After application of Active Prime Fix or Active Prime Grip

→ Uses No Limits:

- adhesive and finishing
- floors and walls
- for internal use - external
- overlaying
- terraces and balconies
- facades
- swimming pools and fountains
- saunas and spa
- domestic
- commercial
- industrial
- street furniture

Do not use on organic-based, reactive waterproofing products (such as RM according to EN 14891).

→ Materials No Limits:

- porcelain tiles
- laminated stoneware
- low thickness slabs
- ceramic tiles
- large ceramic slabs
- marble - natural stone
- recomposed materials
- glass mosaics
- glass tiles
- thermal and acoustic insulation
- terracotta - klinker

Instructions for use

→ Preparation of the substrate

All substrates must be level, cured, undamaged, compact, rigid, resistant, dry and free from any debonding agents and from damp rising. It is good practice to dampen highly absorbent concrete substrates or apply a coat of Active Prime Fix or Active Prime Grip.

→ Preparation

The substrate must comply with current technical regulations and national standards.

Mixing water (EN 12004-2):

Grey:

Normal consistency (EN 12004-2 § 6) = 30% - 32% weight (≈ 7,5-8 l / 1 bag)

Fluid consistency ≈ 36% - 38% weight (≈ 9,0 - 9,5 l / 1 bag)

White Shock:

Normal consistency (EN 12004-2 § 6) = 25% - 27% weight (≈ 6,25 - 6,75 l / 1 bag)

Fluid consistency ≈ 31% - 33% weight (≈ 7,75 - 8,25 l / 1 bag)

Mix Biogel No Limits using clean water until a smooth and lump-free mixture is obtained; leave the mixture to stand for a few minutes and mix again.

Comply with the amounts of water indicated, according to the application to be carried out

→ Application

To guarantee structural adhesion it is necessary to apply a layer of adhesive sufficient to cover the entire back of the coating material.

Instructions for use

Large, rectangular sizes with sides > 60 cm and low thickness sheets may require adhesive to be applied directly to the back of the material. Check samples to make sure the adhesive has been transferred to the back of the material. Respect structural, fractionizing, and perimeter joints present in the substrates. Abide by local existing provisions when creating elastic expansion joints.

- **Cleaning**
Clean the tools and any residues of the product from the surfaces using water while the adhesive is still fresh. Once hardened, the adhesive can only be removed by mechanical means.

Special notes

- **Materials and special substrates**
- **Marble–natural stones and Recomposed materials:** materials that are subject to deformation or staining due to water absorption require a quick-setting or reactive adhesive. Marble and natural stone in general may have characteristics that vary even with reference to materials of the same chemical and physical nature. For this reason it is essential you consult Kerakoll Global Service to request specific indications or to carry out a test on a sample of the material. In the absence of specific indications from the manufacturer, natural stone slabs with reinforcement layers, in the form of resin coating, polymer mesh, matting, etc. or treatments (for example damp courses, etc.) applied on the laying surface must be tested in advance to ensure they are compatible with the adhesive. Check for the presence of any really consistent traces of rock dust created during cutting, and remove them if found.
 - **Waterproofing products:** adherent and floating polymer sheets, liquid bitumen and tar-based sheets or membranes require application of a laying screed on top.
- **Special applications**
- **Facades:** the substrate should guarantee a cohesive tensile strength of $\geq 1.0 \text{ N/mm}^2$.
 - **Always apply a layer of adhesive directly on the back of the material.**

Certificates and marks



* émission dans l'air intérieur Information sur le niveau d'émission de substances volatiles dans l'air intérieur, présentant un risque de toxicité par inhalation, sur une échelle de classe allant de A+ (très faibles émissions) à C (fortes émissions).

| Technical Data compliant with Kerakoll Quality Standard | | |
|--|---|------------|
| Appearance | white or grey pre-mixed powder | |
| Pack | 25 kg | |
| Shelf life | ≈ 12 months in the original packaging in dry environment. Protect from humidity | |
| Thickness | from 2 to 15 mm | |
| Temperature range for application | from +5 °C to +40 °C | |
| Pot life at +23 °C | | |
| - Grey | = 4 h | |
| - White Shock | = 4 h | |
| Open time at +23 °C: | | |
| - Grey | = 30 min. | EN 12004-2 |
| - White Shock | = 30 min. | EN 12004-2 |
| Time required until fully frost-proof: | | |
| - from +5 °C to -5 °C | ≈ 8 h | |
| Foot traffic/grouting of joints at +23 °C: | | |
| - Grey | ≈ 24 h | |
| - White Shock | ≈ 24 h | |
| Grouting in walls at +23 °C: | | |
| - Grey | ≈ 12 h | |
| - White Shock | ≈ 12 h | |
| Ready for use at +23 °C / +5 °C: | | |
| - foot traffic | ≈ 24 h | |
| - heavy traffic | ≈ 3 – 4 days | |
| - swimming pools (+23 °C) | ≈ 14 days | |
| Coverage per mm thickness: | | |
| - Grey (mixing ratio 32%) | ≈ 1.2 kg/m ² | |
| - White Shock (mixing ratio 33%) | ≈ 1.2 kg/m ² | |

Values taken at +23 °C, 50% R.H. and no ventilation. Data may vary depending on specific conditions at the building site, i.e. temperature, ventilation and absorbency level of the substrate and of the materials laid.

Performance**VOC Indoor Air Quality (IAQ) - Volatile organic compound emissions**

| | | |
|------------|-----------------------|-------------------------|
| Conformity | EC 1 plus GEV-Emicode | Cert. GEV 7582/11.01.02 |
|------------|-----------------------|-------------------------|

HIGH-TECH

| | | |
|--|---------------------------|--------------|
| Shear adhesion (porcelain tiles/porcelain tiles) after 28 days | $\geq 2.5 \text{ N/mm}^2$ | ANSI A-118.4 |
|--|---------------------------|--------------|

| | | |
|---|---------------------------|------------|
| Tensile adhesion (concrete/porcelain tiles) after 28 days | $\geq 2.5 \text{ N/mm}^2$ | EN 12004-2 |
|---|---------------------------|------------|

Durability test:

| | | |
|-------------------------------------|-------------------------|----------------|
| - adhesion after heat ageing | $\geq 1 \text{ N/mm}^2$ | EN 12004-2 |
| - adhesion after water immersion | $\geq 1 \text{ N/mm}^2$ | EN 12004-2 |
| - adhesion after freeze-thaw cycles | $\geq 1 \text{ N/mm}^2$ | EN 12004-2 |
| - adhesion after straining cycles | $\geq 1 \text{ N/mm}^2$ | SAS Technology |

| | | |
|---------------|-----------------------|------------|
| Vertical slip | $\leq 0.5 \text{ mm}$ | EN 12004-2 |
|---------------|-----------------------|------------|

| | | |
|-------------------------|-----------------------|------------|
| Transversal deformation | $\geq 2.5 \text{ mm}$ | EN 12004-2 |
|-------------------------|-----------------------|------------|

| | | |
|---------------------|---|--|
| Working temperature | from $-40 \text{ }^\circ\text{C}$ to $+90 \text{ }^\circ\text{C}$ | |
|---------------------|---|--|

| | | |
|------------|----------|----------|
| Conformity | C2 TE S1 | EN 12004 |
|------------|----------|----------|

Values taken at $+23 \text{ }^\circ\text{C}$, 50% R.H. and no ventilation.

Warning

- Product for professional use
- abide by any standards and national regulations
- do not use the adhesive to correct substrate irregularities greater than 15 mm
- protect from direct rainfall for at least 24 hrs
- the temperature, ventilation and absorption of the substrate and covering materials, may vary the adhesive workability and setting times
- use the right size of notched trowel for the format of the tile or slab
- guarantee a full-bed in all external laying operations
- if necessary, ask for the safety data sheet
- for any other issues, contact the Kerakoll Worldwide Global Service - info@kerakoll.ae

The Rating classifications refer to the GreenBuilding Rating Manual 2013. This information was last updated in September 2022 (ref. GBR Data Report - 09.22); please note that additions and/or amendments may be made over time by KERAKOLL SpA; for the latest version, see www.kerakoll.com. KERAKOLL SpA shall therefore be liable for the validity, accuracy and updating of information provided only when taken directly from its institutional website. The technical data sheet given here is based on our technical and practical knowledge. As it is not possible for us to directly check the conditions in your building site and the execution of the work, this information represents general indications that do not bind Kerakoll in any way. Therefore, it is advisable to perform a preliminary test to verify the suitability of the product for your purposes.