

Fugalite Color

Waterproof resin for the grouting and fixing of ceramic tiles, mosaics and natural stone.

Fugalite Color is a next-generation resin that combines the performance of epoxy grout with unparalleled ease of use. Waterproof and designed for grouting and fixing tiles, mosaics and natural stone, it offers chemical resistance and long-lasting colour.



1. Multipurpose - suitable for all tile types and applications
2. Stain-proof - easy to clean
3. Waterproof - ideal for wet environments
4. UV resistant - long lasting colour intensity (CATAS-Tested)
5. Superior workability - easy to mix, apply and clean
6. Certified for food hygiene areas
7. Prevents the growth of bacteria and mould (ISO 846 2019: Method A/B/C)
8. Available in 50 colours

Rating 3

- × Regional Mineral $\geq 30\%$
- ✓ VOC Low Emission
- ✓ Solvent ≤ 5 g/kg
- × Low Ecological Impact
- ✓ Health Care



kerakoll

Areas of application

→ Use

Grouting of joints from 0 to 10 mm with high chemical and mechanical resistance and a high level of hardness. Bonding of glass mosaic.

Materials to be grouted:

- porcelain tiles, low thickness slabs, ceramic tiles, klinker, cotto, glass mosaic, of all types and formats
- natural stone, recomposed materials, marble

Flooring and walls, for internal and external use, domestic, commercial and industrial applications and street furniture subject to permanent or occasional contact with chemical substances, in environments subject to heavy traffic, swimming pools, thermal water baths and fountains, heated floors, also in areas subject to thermal shock and freezing.

Directive CE MED

Grout and adhesive for ceramic tiles, used as an adhesive:

- maximum density per area $1528 \pm 10 \text{ g/m}^2$;
- Thickness as adhesive layer $2 \pm 0.1 \text{ mm}$.

Used as a grout:

- maximum density per area $1363 \pm 10 \text{ g/m}^2$;
- thickness as sealant between tiles $3.9 \pm 0.1 \text{ mm}$.

As finishing material for all exposed interior and concealed or inaccessible surfaces.

The product may be applied to any non-combustible (non-metallic) support having a thickness equal to or greater than 12 mm and a density of $\geq 656 \text{ kg/m}^3$. The product may be applied to any metallic support having a thickness $\geq 2.25 \text{ mm}$. When intended for decks the product may be applied to any metallic support, any non-combustible support or any material having low flame spread characteristics.

Do not use on porous flooring for which more specific or alternative chemical resistances are required compared with those listed in the chemical resistances table, to grout elastic expansion or fractionising joints or on substrates that are not fully dry and subject to moisture rising.

Instructions for use

→ Preparation of substrates:

- As a grout:

Before grouting joints, check that tiles have been laid correctly and are anchored perfectly to the substrate. Substrates must be perfectly dry. Grout joints in accordance with the recommended waiting time indicated on the relative data sheet for the adhesive used. For mortar substrates, wait at least 7 – 14 days depending on screed thickness, ambient weather conditions and on the level of absorption of the covering and the substrate. Any water or moisture rising can cause vapour pressure to accumulate, which may in turn loosen the tiles on account of the complete non-absorbency of the grout or of the tiles themselves. Joints must be free from any excess adhesive, even if already hardened. Furthermore, they must be of an even depth for the whole width of the tile covering, thereby ensuring maximum chemical resistance. Any dust and loose debris must be removed from joints by carefully cleaning them with a vacuum cleaner. The surface of the coating material to be grouted must be dry and free from dust or building dirt; any residual protective coatings must first be removed using specific products.

Before grouting joints, check the cleanability of the tile covering, as porous or highly microporous surfaces may cause cleaning difficulties. Before a tile is laid, it is advisable to perform a preliminary test. If already tiled, test a small, concealed area. In these cases we recommend treating the covering with specific protective products, being careful to avoid applying them to the joints.

- As an adhesive:

Substrates must be compact and solid, free of dust, oil and grease, dry and free from moisture rising, with no loose debris or flaky parts such as residues of cement, lime and paint coatings, which must be completely removed. The substrate must be stable, without cracks and have already completed the curing period of hygro-metric shrinkage. Uneven areas must be corrected with suitable smoothing and finishing products. On screeds and renders/plasters which are highly absorbent and have dusty, flaky surfaces, it is advisable to first apply Active Prime Fix, following the instructions provided in the technical data sheet, in order to reduce the water absorption and improve spreadability of the adhesive.

Instructions for use

→ Preparation

Mix component B with a spatula, pour it all into the bucket of component A, making sure that none of component B is left in the container.

Mix the two components using a low-rev helicoidal agitator ($\approx 400/\text{min.}$) until a smooth, even coloured mixture is obtained. Respect the preset ratio of 2 : 1 of the packaging.

Use a spatula to scrape the walls and bottom of the bucket of component A once component B has been poured into it, so that there are no areas of product that have not been properly mixed.

Mixing by hand is not recommended. The mixture remains workable for approximately 45 mins. (value calculated at $+23\text{ }^{\circ}\text{C}$, R.H. 50%).

→ Application

- As a grout:

Fugalite Color must be applied evenly on the tile covering with a hard rubber grout float. Grout the entire surface until the joints are completely filled, working diagonally to the tiles. If grouting is to be on joints only, it is recommended that a test be carried out in advance before laying to ensure the surface can be properly cleaned. Using the grout float, remove most of the excess grout immediately smoothing it out completely on the surface of the tile.

- As an adhesive:

Fugalite Color can be applied with a suitable toothed spreader, to be chosen according to the size and type of the tile. Using the smooth part of the spreader, apply a fine layer of product, pressing down onto the substrate in order to ensure maximum adhesion, after which the thickness can be adjusted as required by tilting the spreader at an angle. Apply the adhesive to a surface area that will allow laying of the coating material within the open time indicated. Press down using a rubber coated spreader to allow for maximum coverage of the surface.

→ Cleaning

- As a grout:

Preparation

Begin cleaning the tilework when the grout is still fresh.

The addition of Fuga-Wash to the cleaning water: Recommended dosage: 1 measuring cap for every 5 litres of water. For optimal cleaning, use two washboys:

- Use washboy 1 to carry out the first cleaning pass with a cellulose sponge or abrasive felt pad
- Use washboy 2 to carry out the second and final cleaning pass.

Change the washing water frequently so that it is always clean. Replace the sponge or felt pad if they become saturated with product.

First pass

Cleaning with cellulose sponge: clean when the grout is still fresh, using a cellulose sponge dampened with water from the washboy. Use circular movements to soften the film of grout on the tiles and finish the joints. Collect the emulsion formed on the tiles using the sponge. It is important to rinse frequently and make sure clean water is used at all times, using appropriate trays and grills with cleaning rollers (washboy). If necessary, replace the sponge or felt cleaning pad when saturated with grout.

Cleaning with abrasive felt pad for structured surfaces: for more structured surfaces, clean when the grout is still fresh, using a felt pad dampened with water from the washboy. Use circular movements to soften the film of grout on the tiles and finish the joints. Collect the emulsion formed on the tiles using the sponge.

Second pass

Finishing with a cellulose sponge: finish cleaning with a cellulose sponge dampened with water from washboy, working diagonally to the tiles so as not to dig into the joints. Do not walk on the damp floors for at least 12 - 24 hours, to avoid leaving dirt.

Finishing with foam rubber sponge for a smoother joint: for a smooth finish, complete cleaning with a foam rubber-sponge dampened with water from the tray, working diagonally to the tiles so as not to dig into the joints.

Cleaning on the following day:

Once the grout has dried, any traces of dirt and streaks can be removed using Fuga-Soap; to be diluted in accordance with the amount of grout to be removed, and the curing time for Fugalite Color.

Recommended dosage: Fuga-Soap should be diluted with water from 1:1 to 1:3 the following day, or undiluted after 3 days.

Distribute the product over the surface to be treated, using the abrasive felt pad and leaving a thin, even film of liquid. Leave the Fuga-Soap to work between 10 – 30 minutes. After this, clean the surface manually with an abrasive felt pad.

Collect the detergent solution with the sponge, rubber scraper or liquid vacuum system for large surfaces.

Rinse thoroughly with clean water.

Instructions for use

Dry immediately with a dry cloth or liquid vacuum system, without allowing the residual water to evaporate.

Repeat for highly stubborn dirt.

- Special cleaning:

When the grout has hardened (after at least 7 days), any residue can be removed using Fuga-Shock.

Distribute the product diluted in water at a ratio of 1:1 to 1:3, or undiluted on the surface to be treated using an abrasive felt pad. Allow the Fuga-Shock to act for approximately 2 - 5 minutes, then carry out the indicated rinsing and drying operations the day after application.

- As an adhesive:

Residual traces of grout can be removed from tools with water before the product has hardened.

Special notes

→ Adding Fuga-Wash to the cleaning water gives: a better detergent action on coating materials, keeps the sponge cleaner, improves the surface finish of grouting, and cleans effectively without the need for rinsing.

→ Disposal: once component A and B have been mixed it is advised to "back-wash" the component B container with the mixed product to make it inert prior to disposal.

→ Shelf life: it is recommended that the packs are stored at +20 °C for two days prior to use; higher temperatures increase the hardening speed, while lower temperatures make the mix harder to lay and slows down setting.

Certificates and marks



Abstract

High chemical and mechanical resistance grouting of ceramic and porcelain tiles, and glass mosaic will be carried out with a high-slide, easy-to-clean, resin-based grout that is bacteriostatic and fungistatic*, water and stain-proof, for extremely colour-fast joints from 0 to 10 mm in thickness, GreenBuilding Rating 3, such as Fugalite Color by Kerakoll SpA. Joints must be dry and free from traces of adhesive and loose debris. Use a spreader or hard rubber float to apply the grout and suitable sponges and clean water to clean joints on completion. Joints of ____ mm width and tiles ____ x ____ cm in size will give an average coverage of approx. ____ kg/m². Existing elastic expansion and fractionising joints must be respected.

* Tests carried out according to ISO 846: 2019 METHOD A/B/C

Technical Data Compliant with Kerakoll Quality Standard		
Appearance	part A coloured paste / part B neutral paste	
Specific weight	part A ≈ 1.65 kg/dm³ / part B ≈ 1.52 kg/dm³	
Viscosity	≈ 110.000 mPa · s, rotor 93 RPM 10	Brookfield method
Mineralogical nature of inert material	silicate - crystalline	
Chemical nature	epoxy resin (part A) / polyamines (part B)	
Grading	≈ 63 – 250 µm	
Shelf life	≈ 24 months from production in the original sealed packaging	
Warning	protect from frost, avoid direct exposure to sunlight and sources of heat	
Pack	monopack part A 1 kg / part B 0.5 kg monopack part A 2 kg / part B 1 kg	
Mixing ratio	Part A : Part B = 2 : 1	
Specific weight of the mixture	≈ 1.57 kg/dm³	
Pot life at +23 °C	≥ 45 mins.	
Temperature range for application	from +5 °C to +30 °C	
Joint width	from 0 to 10 mm	
Foot traffic	≈ 24 hrs	
Grouting after laying:		
- with Fugalite Color on coating materials	immediate	
- with Fugalite Color on floors	as soon as foot traffic is allowed	
- with adhesive	see characteristics of adhesive	
- mortar	≈ 7 – 14 days	
Interval before normal use	≈ 3 days (mechanical resistance) / ≈ 7 days (chemical resist.)	
Coverage:		
- as an adhesive	≈ 2 – 4 kg/m²	
- as a grout	see Coverage table	

Values taken at +23 °C, 50% R.H. and no ventilation. Data may vary depending on specific conditions at the building site, i.e.temperature, ventilation and absorbency level of the substrate and of the materials laid.

Coverage Table							
		Format	Thickness	grammes/m² joint width			
				1 mm	2 mm	5 mm	10 mm
Mosaic Tiles		2x2 cm	3 mm	471	942	2355	4710
		5x5 cm	4 mm	251	502	1256	2512
Tiles		50x50 cm	4 mm	25	50	125	251
		60x60 cm	4 mm	21	42	105	209
		100x100 cm	4 mm	13	25	63	126
		20x20 cm	8 mm	126	251	628	1256
		30x30 cm	9 mm	94	188	471	942
		40x40 cm	10 mm	79	157	393	785
		30x60 cm	10 mm	79	157	393	785
		60x60 cm	10 mm	52	105	262	523
		60x90 cm	10 mm	44	87	218	436
		100x100 cm	10 mm	31	63	157	314
		120x120 cm	10 mm	26	52	131	262
		20x20 cm	14 mm	220	440	1099	2198
		30x30 cm	14 mm	147	293	733	1465
	Klinker		30x30 cm	15 mm	157	314	785
		12.5x24.5 cm	12 mm	228	455	1138	2276

The data provided must be considered merely as an indication of the grout coverage, averaged out based on our experience and taking into account normal site wastage.
The following may vary according to specific conditions at the building site: roughness of tile, excess of residual product, lack of surface flatness, temperatures, seasonal conditions.

Performance		
VOC Indoor Air Quality (IAQ) - Volatile organic compound emissions		
Conformity	EC 1 plus GEV-Emicode	GEV 17487/11.01.02 cert.
HIGH-TECH		
Static modulus of elasticity	≈ 3000 MPa	ISO 178
Resistance to abrasion	≈ 184 mm ³	EN 12808-2
Water absorption after 240 mins.	≈ 0,05 g	EN 12808-5
Working temperature	from -40 °C to +80 °C	
Colour fastness according to UNI EN ISO 105-A05	see table	
Resistance to fungal contamination	class 0	ISO 846: 2019 METHOD A/B
Resistance to bacterial contamination	class 0	ISO 846: 2019 METHOD C
Porcelain tiles/concrete tensile strength	≥ 5 N/mm ²	EN 1348
Initial shear strength	≥ 15 N/mm ²	EN 12003
Shear strength after water immersion	≥ 15 N/mm ²	EN 12003
Shear strength after thermal shock	≥ 5 N/mm ²	EN 12003
Open time: tensile adhesion	≥ 4 N/mm ²	EN 1346

Values taken at +23 °C, 50% R.H. and no ventilation. Data may vary depending on specific conditions at the building site.

Resistance to stains (ISO 10545-14)		
Staining Agents	Time exposed to staining agent: 24 hours	Time exposed to staining agent: 30 mins.
Red wine	4	5
Olive oil	5	5
Tea	3	5
Coffee	2	5
Cola drink	5	5
Tomato ketchup	5	5
Red fruit jam	5	5
Lemon juice	5	5

Legend:

- 5
- can be cleaned under a running hot tap
- 4
- can be cleaned with a mild detergent while gently rubbing with a sponge
- 3
- can be cleaned with a basic detergent while vigorously rubbing with a sponge
- 2
- to clean, treat first with a solvent or aggressive acid or basic solution, then vigorously rub with a sponge
- 1
- cannot be cleaned by any of the aforementioned methods

Chemical Resistance (EN 12808-1)			
Acids	Concentration	Permanent contact	Occasional contact
Acetic	2,50%
	5%
	10%	.	.
Hydrochloric	37%
Citric	10%
Formic	2,50%	.	.
	10%	.	.
Phosphoric	50%
	75%
Lactic	2,50%
	5%
	10%	.	.
Nitric	25%
	50%	.	.
Oleic	100%	.	.
Sulphuric	50%
	100%	.	.
Tannic	10%
Tartaric	10%

Legend:

- ... excellent
- .. good
- . poor

Values taken at: - ambient +23 °C / 50% R.H. - chemical aggressive agent +23 °C

Chemical Resistance (EN 12808-1)		
Foodstuffs	Main foodstuffs (temporary contact)	
Vinegar	...	
Citrus fruits	...	
Ethyl alcohol	..	
Beer	...	
Butter	...	
Coffee	...	
Casein	...	
Glucose	...	
Animal fat	...	
Fresh milk	...	
Malt	...	
Margarine	...	
Olive oil	...	
Soya oil	...	
Pectin	...	
Tomato	...	
Yoghurt	...	
Sugar	...	
Fuels and Oils	Permanent contact	Occasional contact
Petrol
Diesel oil
Coal tar oil
Mineral oil
Petroleum
Mineral spirit
Turpentine

Legend:

- ... excellent
- .. good
- . poor

Values taken at: - ambient +23 °C / 50% R.H. - chemical aggressive agent +23 °C

Chemical Resistance (EN 12808-1)			
Alkalis and Salts	Concentration	Permanent contact	Occasional contact
Oxygenated water	10%
	25%
Ammonia	25%
Calcium chloride	Saturated Sol.
Sodium chloride	Saturated Sol.
Sodium hypochlorite			
(Active chlorine)	1,50%
	13%	.	.
Caustic soda	50%
Aluminium sulphate	Saturated Sol.
Potassium hydroxide	50%
Potassium permanganate	5%
	10%	.	..
Solvents		Permanent contact	Occasional contact
Acetone		.	.
Ethyl alcohol	
Benzol		.	..
Chloroform		.	.
Methylene chloride		.	.
Ethylene glycol	
Perchloroethylene		.	..
Carbon tetrachloride		.	..
Tetrahydrofuran		.	.
Toluol		.	..
Trichloroethylene		.	.
Xylene		.	..

Legend

- ... excellent
- .. good
- . poor

Values taken at: - ambient +23 °C / 50% R.H. - chemical aggressive agent +23 °C

Fugalite Color - Colour Chart		Special-order colours*	Colour Fastness** GSc (Daylight) EN ISO 105-A05 standard
KK 1		●	4
KK 2			4
KK 4			4
KK 6		●	4
KK 8		●	4
KK 10		●	4.5
KK 12			4.5
KK 26		●	4
KK 27		●	4
KK 29		●	4
KK 30		●	4
KK 55		●	4
KK 47		●	4
KK 50		●	4.5
KK 64		●	4
KK 66			4
KK 68		●	4
KK 69			4
KK 71			4.5
KK 72		●	4.5
KK 76			4
KK 79			4
KK 81		●	4.5
KK 83		●	4.5
KK 86			4.5
KK 88		●	4.5
KK 89			4.5
KK 151		●	4.5
KK 92		●	4.5
KK 93		●	4.5
KK 94		●	4.5
KK 101		●	4.5
KK 102		●	5
KK 154		●	4.5
KK 103		●	5
KK 107			4
KK 109		●	4
KK 110			4
KK 157		●	4
KK 158		●	4.5
KK 153		●	4.5
KK 152		●	4.5
KK 155		●	4.5
KK 114		●	4.5
KK 126		●	4
KK 129		●	4
KK 130		●	4
KK 156		●	4.5
KK 136		●	4
KK 147		●	4.5

Legend: from 5 to 4 high colour fastness; for internal and external use
from 3.5 to 3 good colour fastness; for internal and external use
from 2.5 to 1 limited colour fastness; for internal use

* Special-order colours: subject to a lead time of typically 4-8 weeks

** ageing data 500 hrs Daylight. ISO 11341:2004. GSc (EN ISO 105 A05)

Shades shown are purely indicative.

Warning

- Product for professional use
- abide by any standards and national regulations
- use at temperatures between +5 °C and +30 °C
- use packs which have been stored for 2 – 3 days before use at +20 °C
- respect the mixing ratio of 2 : 1. For partial mixing, weigh the two parts precisely
- workability times may vary considerably, depending on ambient conditions and the temperature of the tiles
- do not walk on floors that are still damp as dirt could still stick to them
- do not lay on substrates subject to moisture rising or which are not completely dry
- if necessary, ask for the safety data sheet
- for any other issues, contact the Kerakoll Worldwide Global Service by calling: 01772 456 831 or emailing: info@kerakoll.co.uk



The Rating classifications refer to the GreenBuilding Rating Manual 2012. This information was last updated in January 2025 (ref. GBR Data Report - 01.25); please note that additions and/or amendments to this information may be made over time by KERAKOLL SpA; for the latest version, see www.kerakoll.com. KERAKOLL SpA shall therefore be liable for the validity, accuracy and updating of information provided only when taken directly from its institutional website. The technical data sheet given here is based on our technical and practical knowledge. As it is not possible for us to directly check the conditions of your building site and the execution of the work, this information represents general indications that do not bind Kerakoll in any way. Therefore, it is advisable to perform a preliminary test to verify the suitability of the product for your purposes.