

Keralevel® Eco LR

Certified, rapid hardening, eco-friendly, mineral levelling product for the high-performance, high-thickness correction of irregular substrates, ideal for use in GreenBuilding. Low CO₂ emissions and very low volatile organic compound emissions, contains locally-sourced recycled raw materials. Recyclable as an inert material at the end of its life.


Keralevel® Eco LR develops a perfect thixotropic balance which is ideal to correct walls that are out of plumb or irregular, and uneven floors without holding up site schedules and subsequent laying of floor/wall coverings.



GREENBUILDING RATING®

Keralevel® Eco LR

- Category: Inorganic mineral products
- Preparation of the substrates



RATING SYSTEM ACCREDITED BY CERTIFICATION BODY SGS

PRODUCT STRENGTHS

- Internal, external
- Thicknesses from 1 to 25 mm
- Prolonged workability, also suitable for large surface areas
- High dimensional stability and long-lasting performance
- High mechanical resistance
- Suitable for laying ceramic tiles, porcelain tiles, natural stone, hardwood floors and resilient materials using adhesives



ECO NOTES

- Formulated with locally-sourced minerals meaning lower greenhouse gas emission during transportation
- Contains recycled minerals thereby reducing the damage to the environment caused by extracting pure raw materials
- Can be recycled as mineral inert material, avoiding waste disposal costs and environmental impact

AREAS OF USE

Use

Levelling correction of irregular and uneven substrates, with rapid setting and drying and compensated shrinkage. Thicknesses from 1 to 25 mm.

Compatible adhesives:

- gel adhesives, mineral adhesives with SAS technology, single and two-component organic adhesives
- reactive-epoxy and polyurethane, single and two-component cement-based adhesives, dispersed in water or solvent solutions

Covering materials:

- porcelain tiles, ceramic tiles, klinker and cotto of all types and formats
- natural stone, recomposed materials, marble
- hardwood flooring, rubber, PVC, linoleum, textiles
- varnishes and paints

Substrates:

- cement plasters and cement-lime mortar
- mineral screeds made with Keracem® Eco Pronto, Keracem® Eco ProntoPlus, Rekord® Eco Pronto and Keracem® Eco as a binder or pre-mixed
- cement-based screeds
- prefabricated concrete or fresh concrete castings
- walls in concrete blocks or cellular concrete
- residual traces of cement-based adhesives

Flooring and walls, for internal and external use, in domestic, commercial and industrial applications, underfloor heating systems.

Do not use

On high flexible substrates subject to thermal expansion, plasterboard, gypsum; on wet surfaces or substrates subject to moisture rising or which are in continuous contact with water.

* ÉMISSION DANS L'AIR INTÉRIEUR Information sur le niveau d'émission de substances volatiles dans l'air intérieur, présentant un risque de toxicité par inhalation, sur une échelle de classe allant de A+ (très faibles émissions) à C (fortes émissions).

INSTRUCTIONS FOR USE

Preparation of substrates

In general, substrates must be free of dust, oil and grease, free from any moisture rising, with no loose, flaky or imperfectly anchored parts such as residues of cement, lime, paint coatings and adhesives, which must be completely removed. The substrate must be stable, non-deformable, without cracks and have already completed the curing period of hygrometric shrinkage.

Low-absorption substrates: smooth substrates with very low absorbency level or which are completely non-absorbent, such as ceramic tiles, marble floor tiles, epoxy and wall paints, residual traces of oxidised adhesives and smoothed concrete coatings which are compact and properly anchored, must be prepared by means of mechanical abrasion or by application of Keragrip Eco, the water-based, eco-friendly adhesion promoter, following the instructions for use and after having carried out thorough cleaning of the surface. Any substances used for surface treatment, such as wax or parting compounds, must be removed mechanically or using specific chemical products.

High-absorbency substrates: on screeds and plasters which are compact but very absorbent, first Primer A Eco, eco-friendly, water-based surface isolation, in order to reduce and regulate the level of absorption. In the case of absorbent substrates with weak consistency, apply Keradur Eco eco-friendly, water-based deep consolidant. Respect the indicated waiting time before carrying out correction of the surface with a levelling product.

Preparation

Prepare Keralevel® Eco LR in a clean container, first of all pouring in a quantity of water equal to approximately $\frac{3}{4}$ of the amount required. Gradually add Keralevel® Eco LR to the container, mixing the paste with a low-rev (≈ 400 /min.) helicoidal agitator. Add more water until the desired consistency is obtained. The mixture must be of smooth consistency and without any lumps. For best results, and to mix larger quantities of levelling product, a stirring device with vertical blades and slow rotation is recommended. Specific polymers with high-dispersion properties ensure that Keralevel® Eco LR is immediately ready for use. The amount of water to be added, indicated on the packaging, is an approximate guide. It is possible to obtain mixtures with consistency of variable thixotropy according to the application to be made. Adding extra water does not improve the workability of the product, and may cause shrinkage in the plastic phase of drying and result in less effective final performance with a reduction in surface hardness, compressive strength and adhesion to the substrate.

Application

Apply a first layer of the product to the suitably prepared and damped substrate using a smooth spreader. Press down hard to ensure adhesion and to force the air out of the pores, after that, the thickness can be adjusted as required. In the event of high thicknesses apply in more layers until the required thickness is obtained. For limited restorations it is possible to work in a single layer, thanks to the high thixotropic effect of the mixture. The appearance of the surface finish may vary depending on whether a smooth steel spreader or a sponge spreader has been used for application. For subsequent laying of ceramic tiles it is always advisable to obtain a roughened, porous surface.

Cleaning

Residual traces of Keralevel® Eco LR can be removed from tools using water before the product hardens.

SPECIAL NOTES

Joints: all the joints located in the substrate must be respected.

Deformable substrates: if substrates are liable to movement, apply the Kerakoll® eco-friendly adhesion promoter suitable for the type of substrate, following the instructions for use. Attach an anti-alkali 4x5 mm size mesh and mix Keralevel® Eco Ultra with ≈ 3 l of Keraplast Eco 337 latex and ≈ 3 l of water.

Gypsum-base plasters: must be dry and prepared with the Primer A Eco eco-friendly, water-based surface insulation, following the instructions for use.

Anhydrite screeds: must be dry and sanded as specified in the manufacturer's instructions, then prepared with water-based, eco-friendly surface isolation Primer A Eco, following the instructions for use.

Large continuous surfaces: continuous, extensive surfaces need to be fractionized with elastic joints so as to create areas of ≈ 50 m². Before laying, it is advisable to apply Keragrip Eco, the eco-friendly adhesion promoter to improve adhesion to the substrate and insert an anti-alkali mesh with 4x5 mm mesh size.

Laying hardwood floors: for subsequent laying of hardwood floors, create a smooth finish with thickness ≥ 3 mm.

ABSTRACT

Certified, high-performance correction of substrates from 1 to 25 mm thickness must be carried out using a fast-acting, high thickness, eco-friendly mineral levelling product, such as Keralevel® Eco LR by Kerakoll Spa, compliant with EN 13813 class CT – C20 – F6, GreenBuilding Rating® 5, suitable for subsequent laying of tiles after ≈ 2 hrs and for laying of natural stone, hardwood floors and resilient materials ≈ 12 hrs after application, at +23 °C 50% R.H.. Apply the product using a smooth spreader on the previously prepared, clean and dimensionally stable substrate and finish with a rigid float. Average coverage: ≈ 1.3 kg/m² per mm of thickness created.

TECHNICAL DATA COMPLIANT WITH KERAKOLL QUALITY STANDARD

Appearance	pre-mixed	
Apparent volumetric mass	≈ 1,45 kg/dm ³	UEAtc/CSTB 2435
Mineralogical nature of inert material	silicate - crystalline carbonate	
Grading	≈ 0 – 600 µm	UNI 10111
Shelf life	≈ 6 months in the original packaging in dry environment	
Pack	25 kg bags	
Mixing water	≈ 6 l / 1 25 kg bag	
Specific weight of the mixture	≈ 1.62 kg/dm ³	UNI 7121
Pot life	≥ 20 min.	
Temperature range for application	from +5 °C to +30 °C	
Maximum thickness	from 1 mm to 25 mm	
Foot traffic	≈ 2 hrs	
Waiting time before laying:		
- ceramic tiles, terracotta	≈ 2 hrs	
- hardwood floors, resilient materials and natural stone		≈ 12 hrs
Coverage	≈ 1.3 kg/m ² per mm of thickness	

Values taken at +20 °C, 65% R.H. and no ventilation. Data may vary depending on specific conditions at the building site, i.e. temperature, ventilation and absorbency level of the substrate.

PERFORMANCE

VOC INDOOR AIR QUALITY (IAQ) - VOLATILE ORGANIC COMPOUND EMISSIONS

Conformity	EC 1 plus GEV-Emicode	GEV certified 2951/11.01.02
HIGH-TECH		
Adhesion to concrete after 28 days	≥ 1 N/mm ²	EN 13892-8
Resistance to:		
- compressive strength after 28 days	≥ 20 N/mm ²	EN 13892-2
- flexural after 28 days	≥ 6 N/mm ²	EN 13892-2
- abrasion after 28 days	≤ 250 mm ³	EN 12808-2
Surface hardness after 28 days	≥ 30 N/mm ²	EN 13892-6
Conformity	CT – C20 – F6	EN 13813

Values taken at +20 °C, 65% R.H. and no ventilation. Data may vary depending on specific conditions at the building site.

WARNING

- **Product for professional use**
- abide by any standards and national regulations
- do not use Keralevel® Eco LR for levelling purposes or for the correction of substrate irregularities greater than 25 mm
- do not add other binders or additives to the mixture
- low temperatures and high relative humidity lengthen drying times
- an excessive quantity of water will reduce strength and the drying time
- before laying hardwood floors and resilient materials, check residual moisture with a calcium carbide hygrometer
- protect from direct sunlight and currents of air for the first 12 hrs
- respect the elastic joints present in the substrate
- if necessary, ask for the safety data sheet
- for any other issues, contact the Kerakoll Worldwide Global Service +39 0536 811 516 - globalservice@kerakoll.com

The Rating classifications refer to the GreenBuilding Rating® Manual 2013. This information was last updated in November 2019 (ref. GBR Data Report - 12.19); please note that additions and/or amendments may be made over time by KERAKOLL SpA, for the latest version, see www.kerakoll.com. KERAKOLL SpA shall therefore be liable for the validity, accuracy and updating of information provided only when taken directly from its institutional website. The technical data sheet given here is based on our technical and practical knowledge. As it is not possible for us to directly check the conditions in your building yards and the execution of the work, this information represents general indications that do not bind Kerakoll in any way. Therefore, it is advisable to perform a preliminary test to verify the suitability of the product for your purposes.



KERAKOLL
The GreenBuilding Company

KERAKOLL S.p.a.
Via dell'Artigianato, 9 - 41049 Sassuolo (MO) Italy
Tel +39 0536 816 511 - Fax +39 0536 816 581
info@kerakoll.com - www.kerakoll.com