

# Nanodefense Eco

Certified, eco-friendly, organic, water-based, mineral waterproofing product for absorbent substrates in damp environments.

Nanodefense Eco develops total water-resistance under positive thrust guaranteeing the protection of absorbent substrates or those subject to damp, or in constantly humid environments.



## Rating 5

1. Suitable for subsequent laying of ceramic tiles, porcelain tiles and natural stone using mineral adhesives
2. High elasticity and chemical stability
3. It can be easily applied with a spreader or roller to any substrate

- ✓ Regional Mineral  $\geq 30\%$
- ✓ VOC Low Emission
- ✓ Solvent  $\leq 5$  g/kg
- ✓ Low Ecological Impact
- ✓ Health Care

---

## Areas of application

### → Use

Waterproofing of smooth, compact and absorbent substrates before laying ceramic coverings with adhesives.

Compatible adhesives:

- gel-adhesives, mineral adhesives and mineral adhesives with SAS technology
- single-component and two-component organic mineral adhesives
- cement-based, water-dispersed, reactive-epoxy and polyurethane two-component adhesives

For internal use. Concrete flooring, compact and smooth cement-based screeds, prefabricated or fresh concrete castings, gypsum, plasterboard and gypsum brick walls, cement-based plasters and finishing products and cement-lime mortar.

- Do not use in external applications, on wet surfaces or substrates subject to moisture rising; in environments where water is always present, baths, swimming pools and tanks.

---

## Instructions for use

### → Preparation of substrates

Substrates must comply with BS 5385, parts 1-5, be compact, smooth and absorbent, free from dust, oil and grease, free from moisture rising, with no loose and inconsistent debris. Varnishes and paints must be removed completely. The substrate must be stable, non-deformable and with no cracks. Cement-based substrates must have a residual humidity  $\leq 2\%$  CM. Plasters with a gypsum base must present a residual humidity  $\leq 1\%$  CM, and screeds with an anhydrite base  $\leq 0.5\%$  CM, or  $\leq 0.3\%$  CM if an underfloor heating system is installed; measurements should be carried out with a calcium carbide hygrometer. Check for traces of thin finishing, that would interfere with the subsequent laying of heavy surface coverings such as ceramic tiles.

### → Preparation

Nanodefense Eco is ready for use. In any case, before use it is advisable to remix the product inside the pack to ensure the mixture is of an even consistency. Any excess waterproofing product can be kept for later use by putting the lid back on the packaging.

### → Application

Apply a fine, uniform film, preferably using a short bristle, synthetic fibre roller, a steel spreader or brush. When applied with a roller or brush, wait until the first coat has hardened before proceeding with the second one ( $\approx 1$  hr depending on the absorbency level of the substrate and temperature) in order to ensure waterproofing. The distinct light blue colouring of Nanodefense Eco allows the user to check whether the application is complete and uniform. Angles and hydraulic couplings must be joined respectively using Aquastop 120 waterproof treatment and relative accessories applied directly with Nanodefense Eco.


### → Cleaning

Nanodefense Eco can be removed from tools and other surfaces by washing them using water before the product hardens or with solvents once hardened.

## Special notes

- On highly absorbent substrates, apply a base coat by diluting Nanodefense Eco with water depending on substrate absorption (max 5%). After this, apply the second undiluted coat using a steel spreader or roller to ensure the watertightness of the surface.
- If necessary, Aquastop AR1 special reinforcing mesh made of alkali-resistant glass fibre can be inserted, followed by a further coat of Nanodefense Eco.

## Certificates and marks



HERAKOLL S.p.A. Sassuolo  
Verbandsmitglied  
P. 87681901.201 - P. 87681902.201  
P. 99902101.201  
Sturmfliciesen-Vereinigung e. V., Burgwedel  
Verbandsmitglied A  
gemäß Prüfungsregeln

### Technical Data compliant with Kerakoll Quality Standard

Appearance	light blue paste	
Specific weight	≈ 1.44 kg/dm <sup>3</sup>	
Chemical nature	co-polymers dispersed in water	
Shelf life	≈ 12 months from production in the original sealed packaging	
Warning	protect from frost, avoid direct exposure to sunlight and sources of heat	
Pack	15 / 5 kg buckets	
Viscosity	≈ 1,100,000 mPa · s, rotor 93 RPM 0.5	Brookfield method
Temperature range for application	from +5 °C to +35 °C	
Dilution for base coat	≈ 5%	
Minimum thickness per coat	≈ 1 mm	
Minimum dry thickness per coat	≈ 500 µm	
Waiting time between 1 <sup>st</sup> and 2 <sup>nd</sup> coat	≈ 1 hr	
Waiting time before laying:		
- min.	≥ 2 hrs	
- max	≤ 48 hrs	
Coverage	≈ 1.5 kg/m <sup>2</sup>	

Values taken at +23 °C, 50% R.H. and no ventilation.

**Performance****VOC Indoor Air Quality (IAQ) - Volatile organic compound emissions**

Conformity	EC 1 plus GEV-Emicode	GEV certified 2134/11.01.02
------------	-----------------------	--------------------------------

**HIGH-TECH**

Water-resistance	≥ 3 bar	DIN 1048
Permeability to water vapour $\mu$ after 28 days	≥ 20000	Cert.173379 Inst. Giordano
Water absorption after 28 days	≤ 5%	UNI 8202/22
Adhesion to concrete after 28 days	≥ 1 N/mm <sup>2</sup>	EN 1542
Tensile strength after 28 days:		
- adhesives Class C1	≥ 0.5 N/mm <sup>2</sup>	EN 1348
- adhesives Class C2	≥ 1 N/mm <sup>2</sup>	EN 1348
Elongation at break after 7 days	≥ 90%	DIN 53 504
Crack bridging	≥ 1.5 mm	ASTM C 1305
Working temperature	from -40 °C to +90 °C	
Conformity	CSTB	13/12-1142

Values taken at +23 °C, 50% R.H. and no ventilation. Data may vary depending on specific conditions at the building site.

## Warning

- Product for professional use
- abide by any standards and national regulations
- do not apply Nanodefense Eco as an external waterproofing covering
- use at temperatures between +5 °C and +35 °C
- it should be stored and transported at temperatures of more than +5 °C
- apply the subsequent coat only when the previous one is perfectly dry
- if necessary, ask for the safety data sheet
- for any other issues, contact the Kerakoll Worldwide Global Service 01772 456 831 - info@kerakoll.co.uk



The Rating classifications refer to the GreenBuilding Rating Manual 2012. This information was last updated in December 2022 (ref. GBR Data Report – 12.22); please note that additions and/or amendments may be made over time by KERAKOLL SpA; for the latest version, see [www.kerakoll.com](http://www.kerakoll.com). KERAKOLL SpA shall therefore be liable for the validity, accuracy and updating of information provided only when taken directly from its institutional website. The technical data sheet given here is based on our technical and practical knowledge. As it is not possible for us to directly check the conditions in your building yards and the execution of the work, this information represents general indications that do not bind Kerakoll in any way. Therefore, it is advisable to perform a preliminary test to verify the suitability of the product for your purposes.